

**METHODS OF PLANARIZING STRUCTURES ON WAFERS**  
**AND SUBSTRATES BY POLISHING**

**ABSTRACT OF THE DISCLOSURE**

5                   Methods of planarizing structures formed on the surfaces of substrates  
and wafers are disclosed. The methods form a planarizing layer over the surface and  
the structures, or the locations where the structures are to be formed, such that the top  
surface of the layer has low areas between the locations of the structures, and such that  
the low areas lie substantially within a plane which is below the tops of the structures.  
10                  A polish-stop layer is then formed over the low areas of the planarizing layer, the  
polish-stop layer being more resistant to polishing than the planarizing layer and,  
preferably, the structures. The resulting surface is then polished. The polishing may  
be accomplished by, for example, standard mechanical polishing, and chemical-  
mechanical polishing.

15